



Uniting everyone,
everything, everywhere.

EGENSKAPER FÖR GUMMI

som används på MPC-slangklämmor och kopplingar.

TABLE OF CONTENTS

Allmänna egenskaper för gummi	3
Egenskaper hos gummiföreningarna	4
Kemisk resistens hos gummiföreningarna	5

Gummimaterialet som listas i denna översikt beskriver de som för närvarande används av MPC. Det fungerar endast som referens för användaren och innebär inte på något sätt att MPC krävs för att använda dessa listade gummimaterial. När råvarupriserna rör sig och ny teknik dyker upp förbehåller sig MPC rätten att ändra råmaterial och processer som används i våra produkter så länge MPC kan visa att den totala produktprestanda och kemiska resistens inte har försämrats.



ALLMÄNNNA EGENSKAPER FÖR GUMMI

ASTM Benämning förkortning	EPDM, EP, EPT, EPR	NBR	CR	VMQ, PMQ, PVMQ	FKM, FEPM
Kemiskt namn	Ethylene Propylene	Acrylonitrile Butadiene	Polychloroprene	Sillicone	Fluorocarbon
Populära namn	EPDM	Nitrile	Neoprene	Sillicone	Viton
Används på MPC-klämmor	"HC-ESA" Heavy Duty Clamp - European Standard "HC-AS" Heavy Duty Clamp - American Standard "LC" Light Duty Clamp "SB" Support Brackets "DL" Pipe Mounting strengthened "SL" Pipe Mounting firm M6	På förfrågan På förfrågan På förfrågan På förfrågan På förfrågan På förfrågan	På förfrågan På förfrågan På förfrågan På förfrågan På förfrågan	På förfrågan På förfrågan På förfrågan På förfrågan På förfrågan	På förfrågan På förfrågan På förfrågan På förfrågan På förfrågan
Används på "U-connect" -kopplingar	Alla U-connect- kopplingar	Alla U-connect- kopplingar	-	På förfrågan	På förfrågan

Gummimaterialet som listas i denna översikt beskriver de som för närvarande används av MPC. Det fungerar endast som referens för användaren och innebär inte på något sätt att MPC krävs för att använda dessa listade gummimaterial. När råvarupriserna rör sig och ny teknik dyker upp förbehåller sig MPC rätten att ändra råmaterial och processer som används i våra produkter så länge MPC kan visa att den totala produktprestanda och kemiska resistens inte har försämrats.

EGENSKAPER HOS GUMMIFÖRENINGARNA

A Bra - Utmärkt

B Rimligt - Bra

C Dålig

X Använd inte



Allmänt temperaturområde i Celsius

Allmänt temperaturområde i Fahrenheit

**Specifikt temperaturområde för "U-connect"
-kopplingar i Celsius:**

**Specifikt temperaturområde för "U-connect"
-kopplingar i Fahrenheit**

Hårdhet "Shore A" (+5 / -5)

Värm åldrande vid 100 °C (212 °F)

Ångbeständighet

Vädermotstånd

Motstånd mot solljus

Ozonresistens

Vattentålighet

Vibrationsdämpning

Slidmotstånd

	EPDM	NBR	CR	VMQ-PVMQ	FKM
Allmänt temperaturområde i Celsius	-55 - 130	-35 - 110	-45 - 120	-55 - 230	-20 - 326
Allmänt temperaturområde i Fahrenheit	-67 - 266	-30 - 230	-49 - 248	-67 - 446	-40 - 410
Specifikt temperaturområde för "U-connect" -kopplingar i Celsius:	-30 - 110	-20 - 80	-	-40 - 220	-18 - 300
Specifikt temperaturområde för "U-connect" -kopplingar i Fahrenheit	-22 - 230	-4 - 176	-	-40 - 428	-0.4 - 572
Hårdhet "Shore A" (+5 / -5)	60	60	60	60	60
Värm åldrande vid 100 °C (212 °F)	A	B	A	A	A
Ångbeständighet	A	A	B	B	C
Vädermotstånd	A	B	B	A	A
Motstånd mot solljus	A	B	B	A	A
Ozonresistens	A	B	B	A	A
Vattentålighet	A	A	B	A	A
Vibrationsdämpning	B	B	A	B	B
Slidmotstånd	B	A	A	C	B

Gummimaterialet som listas i denna översikt beskriver de som för närvarande används av MPC. Det fungerar endast som referens för användaren och innebär inte på något sätt att MPC krävs för att använda dessa listade gummimaterial. När råvarupriserna rör sig och ny teknik dyker upp förbehåller sig MPC rätten att ändra råmaterial och processer som används i våra produkter så länge MPC kan visa att den totala produktprestanda och kemiska resistens inte har försämrats.

KEMISK RESISTENS HOS GUMMIFÖRENINGARNA

A Bra - Utmärkt

B Rimligt - Bra

C Dålig

X Använd inte



Kontakta fluid

10% Hydrated ammonium	Inorganic base
10% Hypochlorite sodium (aqueous solution)	Inorganic salt
25% Oxalic acid at 80 °C (176 °F)	Organic acid
50% Fluoridic acid	Inorganic acid
65% Concentrated nitric acid	Inorganic acid
65% Fluoridric acid at 60 °C (140 °F)	Inorganic acid
75% Fluoridic acid	Inorganic acid
90% Oxygen water	Inorganic peroxide

EPDM

NBR

CR

VMQ-PVMQ

FKM

A

Acetaldehyde	Aldehyde
Acetamide 100 °C (212 °F)	Amide
Acetate lead (aqueous solution)	Organic salt
Acetic acid at 25% at 100 °C (212 °F)	Organic acid
Acetic anhydride	Organic anhydride
Acetone	Ketone
Acetophenone	Ketone

A

X

CX

AB

X

A

B

B

BC

A

A

B

B

X

-

X

X

X

BC

X

B

C

AB

C

X

A

X

BC

B

X

A

X

X

CX

X

Gummimaterialet som listas i denna översikt beskriver de som för närvarande används av MPC. Det fungerar endast som referens för användaren och innebär inte på något sätt att MPC krävs för att använda dessa listade gummimaterial. När råvarupriserna rör sig och ny teknik dyker upp förbehåller sig MPC rätten att ändra råmaterial och processer som används i våra produkter så länge MPC kan visa att den totala produktprestanda och kemiska resistens inte har försämrats.

KEMISK RESISTENS HOS GUMMIFÖRENINGARNA

Kontakta fluid	Typ	EPDM	NBR	CR	VMQ-PVMQ	FKM
Acetylene	Hydrocarbon	A	AB	B	BC	A
Acrylonitrile at 50 °C (122 °F)	Nitrile	C	X	BC	CX	X
Adipic acid	Organic acid	A	A	A	-	A
Alum	Inorganic salt	A	A	A	AB	-
Aluminum sulphate	Inorganic salt	A	A	A	A	A
Amile acetate	Ester	B	X	X	X	X
Amile borato	Ester	X	A	A	-	A
Ammonia gassosa	Inorganic base	A	A	A	A	X
Ammonium carbonate at 80 °C sol. Watery	Inorganic salt	A	CX	AB	BC	-
Ammonium chloride (aqueous solution)	Inorganic salt	A	A	A	A	A
Ammonium nitrate (aqueous solution)	Inorganic salt	A	AB	AB	A	A
Ammonium nitrite (aqueous solution)	Inorganic salt	A	A	A	B	-
Ammonium persulphate (aqueous solution)	Inorganic salt	A	-	A	A	-
Ammonium sulphate (aqueous solution)	Inorganic salt	A	A	A	A	-
Amylic alcohol at 50 °C (122 °F)	Alcohol	A	B	A	BC	AB
Anhydro fluoridic acid	Inorganic acid	C	X	C	X	C
Anhydrous bromo	Inorganic compound	X	X	X	X	A
Aniline	Aromatic organic base	AB	X	C	A	AB
Aniline at 100 °C (212 °F)	Aromatic organic base	B	X	X	AB	C
Aqua regia	Inorganic acid	C	X	CX	CX	B
Arsenico tricoloruro	Inorganic salt	C	A	A	-	-
Astm oil n. 1 At 100 °C (212 °F)	Mineral oil	X	A	A	AB	A
Astm oil n. 2 At 100 °C (212 °F)	Mineral oil	X	A	B	B	A
Astm oil n. 3 At 100 °C (212 °F)	Mineral oil	X	A	CX	C	A
B						
Bakery gas	Gas	C	BC	C	A	A
Barium hydrate (saturated aqueous solution)	Inorganic base	A	A	A	A	A
Barium sulphate	Inorganic salt	A	A	A	A	A
Beer	Alcoholic food	A	A	A	A	A
Benzene	Aromatic hydrocarbon	X	CX	X	X	AB

A Bra - Utmärkt

B Rimligt - Bra

C Dålig

X Använd inte

KEMISK RESISTENS HOS GUMMIFÖRENINGARNA

Kontakta fluid	Typ	EPDM	NBR	CR	VMQ-PVMQ	FKM
Benzile chloride	Chlorinated aromatic hydrocarbon	X	X	X	C	A
Benzoic acid	Organic acid	C	C	X	C	A
Benzoic aldehyde	Aldehyde	A	X	X	-	CX
Benzoic aldehyde at 100 °C (212 °F)	Aldehyde	A	X	X	-	X
Benzol	Aromatic hydrocarbon	X	CX	X	X	AB
Benzyl alcohol	Alcohol	A	X	BC	AB	A
Bitumen	Hydrocarbon	X	B	C	BC	A
Borace (aqueous solution)	Inorganic salt	A	B	AB	B	A
Boric acid at 10% at 100 °C (212 °F)	Inorganic acid	A	A	A	B	A
Butadiene	Hydrocarbon	C	X	CX	X	AB
Butanone	Ketone	A	X	C	CX	X
Butyl acetate	Ester	BC	X	X	X	X
Butyl acetyl ricinoleate	Ester	A	-	-	-	-
Butyl alcohol at 100 °C (212 °F)	Alcohol	-	A	C	X	B
Butyl alcohol at 50 °C (122 °F)	Alcohol	AB	A	A	B	A
Butyl benzoate	Ester	A	X	X	-	A
Butyl carbitol	Alcohol	A	A	BC	-	A
Butyl cellosolve	Alcohol	A	C	BC	-	X
Butyl lactate	Ester	-	B	-	-	-
Butyl oiled	Ester	BC	BC	X	-	A
Butyl phthalate	Ester	AB	X	X	B	BC
Butyl stearate at 70 °C (158 °F)	Ester	C	B	X	AB	A
Butyric acid	Organic acid	BC	BC	C	-	BC
C						
Calcium hydrate (aqueous suspension)	Inorganic base	A	AB	A	BC	A
Carbitol	Alcohol	AB	BC	BC	B	B
Carbon dioxide	Inorganic anhydride	AB	AB	AB	AB	A
Carbon sulphide	Carbon sulphide	X	C	X	X	A
Carbon tetrachloride	Chlorinated hydrocarbon	X	C	X	X	A
Carbonic acid	Inorganic acid	A	B	A	A	A
Castor oil	Oils	A	B	C	A	A
Cellosolve	Alcohol	B	-	-	-	C
Cellosolve acetate	Ester	B	X	X	X	X

A Bra - Utmärkt

B Rimligt - Bra

C Dålig

X Använd inte

KEMISK RESISTENS HOS GUMMIFÖRENINGARNA

Kontakta fluid	Typ	EPDM	NBR	CR	VMQ-PVMQ	FKM
Chloride iron (aqueous solution)	Inorganic salt	A	A	A	AB	A
Chloroacetic acid 25%	Organic acid	AB	CX	C	X	X
Chloroacetone	Ketone	A	X	BC	C	X
Chlorobenzene	Chlorinated aromatic hydrocarbon	X	X	X	X	A
Chloroform	Chlorinated hydrocarbon	X	X	X	CX	A
Chrome plating baths	Inorganic salts	B	X	X	B	A
Chromic acid at 50% at 50 °C (122 °F)	Inorganic acid	BC	X	X	X	A
Citric acid 33%	Organic acid	A	AB	A	A	A
Clorobromometano	Chlorinated hydrocarbon	BC	X	X	X	A
Clorobutadiene	Chlorinated hydrocarbon	X	X	X	X	A
Clorodifenile	Chlorinated aromatic hydrocarbon	X	X	X	B	A
Cockery gas	Gas	C	C	C	AB	A
Coconut oil	Oils	BC	A	B	A	A
Cold hydrogen sulfur (aqueous solution)	Inorganic acid	A	X	A	C	X
Cold oxygen	Gas	A	B	A	A	A
Concentrated hydrate ammonium	Inorganic base	A	B	A	A	B
Copper sulphate (aqueous solution)	Inorganic salt	A	A	A	A	A
Cotton oil	Oils	B	A	BC	BC	A
Creosote	Phenol	X	AB	BC	X	A
Cresol	Phenol	BC	CX	C	-	AB
Crotonaldehyde	Aldehyde	A	A	A	X	A
Cyanidric acid at 20%	Inorganic acid	A	C	C	BC	A
Cyclohexane	Hydrocarbon	X	A	CX	X	A
Cyclohexanone	Ketone	B	X	X	C	X
D						
Decalin	Hydrocarbon	X	BC	X	CX	A
Diacetone	Ketone	A	X	AB	AB	X
Dibenzyl ether	Aromatic ether	B	X	CX	B	-
Dicloroisopropiletere	Ether	C	X	X	X	C
Diesel	Hydrocarbon	X	A	BC	X	A

A Bra - Utmärkt

B Rimligt - Bra

C Dålig

X Använd inte

KEMISK RESISTENS HOS GUMMIFÖRENINGARNA

Kontakta fluid	Typ	EPDM	NBR	CR	VMQ-PVMQ	FKM
Diethanolamine	Organic base	A	BC	-	-	-
Diethylamine	Organic base	C	BC	BC	BC	X
Diethylene glycol	Alcohol	A	A	A	AB	A
Diisobutylene	Hydrocarbon	X	B	CX	X	A
Diisopropylcheton	Ketone	AB	X	X	X	X
Diisopropylbenzene	Aromatic hydrocarbon	X	X	X	B	A
Dimethylamine	Organic base	B	X	X	X	X
Dimethylaniline	Aromatic organic base	B	X	CX	-	X
Dimethylformamide	Amide	B	BC	C	AB	X
Diethyl	Aromatic ester	B	C	X	BC	A
Diethylsebacato	Ester	B	X	X	C	A
Dioxane	Ether	B	X	X	-	X
Diphenyl	Aromatic hydrocarbon	X	CX	X	C	A
Diphenyl oxide	Aromatic ether	X	X	X	BC	A
Distilled water at 100 °C (212 °F)	Water	A	AB	B	AB	AB
Dowtherm	Aromatic ether	X	X	X	BC	A
Dry chlorine	Inorganic compound	CX	C	C	X	AB

E

Epichlorhydrin	Chlorinated hydrocarbon	B	X	X	X	X
Esaldeide	Aldehyde	A	X	A	B	CX
Ethane	Hydrocarbon	X	A	B	X	A
Ethanolamine	Organic base	A	A	B	B	X
Ethyl acetate	Ester	A	X	C	A	X
Ethyl acetoacetate	Ester	B	X	C	B	X
Ethyl alcohol at 50 °C (122 °F)	Alcohol	A	A	A	A	B
Ethyl benzoate	Ester	B	X	X	X	A
Ethyl chloride	Chlorinated hydrocarbon	B	B	BC	X	A
Ethyl ether	Ether	C	BC	X	X	X
Ethyl lactate	Ester	-	B	-	-	-
Ethyl mercaptan	Mercaptan	CX	X	CX	C	B
Ethyl silicate	Ester of silicic acid	A	A	A	A	A
Ethylcellosolve	Alcohol	B	X	X	X	X
Ethylene	Hydrocarbon	X	A	BC	-	A
Ethylene chloride	Chlorinated hydrocarbon	C	CX	X	CX	B
Ethylene glycol	Alcohol	A	A	A	A	A
Ethylene oxide at -20 °C (68 °F)	Hydrocarbon	BC	X	X	C	X
Ethylenediamine	Organic base	AB	AB	AB	C	X

A Bra - Utmärkt

B Rimligt - Bra

C Dålig

X Använd inte

KEMISK RESISTENS HOS GUMMIFÖRENINGARNA

Kontakta fluid	Typ	EPDM	NBR	CR	VMQ-PVMQ	FKM
Ethylenglycol at 100 °C (212 °F)	Alcohol	A	A	B	A	A
F						
Fluid A (isooctane)	Hydrocarbon	X	A	AB	X	A
Fluid B (70% isooctane - 30% toluene)	Aromatic hydrocarbon	X	AB	C	X	A
Fluid C (50% isooctane - 50% toluene)	Aromatic hydrocarbon	X	B	X	X	A
Fluorobenzene	Fluorinated aromatic hydrocarbon	X	X	X	X	A
Fluorosilicic acid	Inorganic acid	B	B	B	X	B
Formaldehyde at 40% at 20 °C (68 °F)	Aldehyde	A	BC	AB	AB	A
Formaldehyde at 40% at 70 °C (158 °F)	Aldehyde	-	X	-	-	-
Formic acid at 23 °C (73 °F) (saturated solution)	Organic acid	B	B	B	B	C
Formic acid at 75 °C (167 °F) (saturated sol)	Organic acid	B	C	C	X	X
Freon 11	Freon	X	AB	B	X	C
Freon 112	Freon	X	B	BC	X	A
Freon 113	Freon	CX	A	A	X	B
Freon 114	Freon	A	A	A	X	B
Freon 114 / B2	Freon	X	B	A	-	B
Freon 115	Freon	A	A	A	C	B
Freon 12	Freon	B	A	A	X	B
Freon 13	Freon	A	A	A	X	AB
Freon 142 / B	Freon	AB	A	A	X	X
Freon 152 / A	Freon	A	A	A	-	X
Freon 21	Freon	X	X	BC	X	X
Freon 218	Freon	A	A	A	-	A
Freon 22	Freon	A	CX	A	X	X
Freon 31	Freon	A	X	AB	X	X
Freon 32	Freon	A	A	A	C	CX
Freon 502	Freon	A	B	A	C	B
Freon BF	Freon	X	B	BC	X	A
Freon C 316 and C / 318	Freon	A	A	A	X	AB
Freon MF	Freon	X	A	C	X	B

A Bra - Utmärkt

B Rimligt - Bra

C Dålig

X Använd inte

KEMISK RESISTENS HOS GUMMIFÖRENINGARNA

Kontakta fluid

Freon T-WD-602

Freon TA

Freon TC

Freon TF

Freon TMC

Freon TP 35

Furfural

Typ

Freon

Freon

Freon

Freon

Freon

Freon

Alcohol

EPDM

B

AB

B

X

BC

A

B

NBR

B

A

A

A

B

A

X

CR

B

AB

A

A

BC

A

C

VMQ-PVMQ

X

-

-

X

C

A

CX

FKM

X

C

A

AB

A

A

X

G

Gallic acid

Gasohol (toluene 50% -

isooctane 30% - methanol 20%)

Glacial acetic acid

Glucose

Glue

Glycerine

Organic acid

Aromatic hydrocarbon and alcohol

Organic acid

Alcohol

Organic compound

Alcohol

B

X

A

A

A

A

C

C

C

A

A

A

BC

X

C

A

A

A

A

-

BC

A

A

A

A

-

X

A

A

A

H

Helium

Hexane

Hexanol

Hexene

Hot gas ammonia

Hot hydrogen sulfur

(aqueous solution)

Hybrid acid 40%

Hydrazine

Hydrochloric acid 10%

Hydrochloric acid at 37%

Hydrochloric acid at 37% at 70 °C (158 °F)

Hydrogen

Hydroquinone

Hypochlorite calcium

(aqueous solution)

Hypochlorite sodium at 10%

at 100 °C (212 °F) (aqueous solution)

Gas

Hydrocarbon

Alcohol

Hydrocarbon

Inorganic base

Inorganic acid

Inorganic acid

Hydrazine

Inorganic acid

Inorganic acid

Inorganic acid

Gas

Phenol

Inorganic salt

Inorganic salt

A

CX

C

X

B

A

A

A

A

A

BC

A

B

A

-

A

A

A

B

CX

X

CX

B

B

B

AB

A

C

C

-

A

B

B

B

AB

BC

B

B

AB

BC

X

A

X

C

-

A

X

BC

X

A

C

X

C

C

CX

X

BC

-

B

-

A

A

A

A

X

X

A

X

A

A

AB

A

X

A

X

A Bra - Utmärkt

B Rimligt - Bra

C Dålig

X Använd inte

KEMISK RESISTENS HOS GUMMIFÖRENINGARNA

Kontakta fluid	Typ	EPDM	NBR	CR	VMQ-PVMQ	FKM
I						
Iodine pentafluoride	Inorganic compound	X	X	X	X	X
Iodoformio	Hydrocarbon	A	-	-	-	-
Isobutyl alcohol	Alcohol	A	B	A	A	A
Isopropyl alcohol	Alcohol	A	B	A	AB	A
Isopropylic ether	Ether	CX	B	BC	X	X
J						
Jelly	Food	A	A	A	A	A
Jp - 4	Hydrocarbon	X	A	BC	X	A
K						
Kerosene	Hydrocarbon	X	A	BC	X	A
L						
Lactic acid	Organic acid	AB	BC	BC	A	A
Lardo at 70 °C (158 °F)	Food	C	A	B	BC	A
Lead free petrol	Hydrocarbon	X	AB	C	X	A
Ligroine	Hydrocarbon	X	A	B	X	A
Linseed oil	Oils	A	A	B	B	A
Liquid ammonia	Inorganic base	A	AB	AB	CX	X
Liquid butane	Hydrocarbon	X	A	AB	X	A
Liquid fluorine	Inorganic compound	CX	X	X	X	B
Liquid propane	Hydrocarbon	X	A	B	C	A
Lithium bromide (aqueous solution)	Inorganic salt	A	A	A	A	A
M						
Magnesium hydrate (aqueous suspension)	Inorganic base	A	B	A	A	A
Magnesium sulphate (aqueous solution)	Inorganic salt	A	A	A	A	A
Maleic acid	Organic acid	BC	C	C	X	A

A Bra - Utmärkt

B Rimligt - Bra

C Dålig

X Använd inte

KEMISK RESISTENS HOS GUMMIFÖRENINGARNA

Kontakta fluid	Typ	EPDM	NBR	CR	VMQ-PVMQ	FKM
Maleic anhydride	Organic anhydride	C	X	C	-	-
Malic acid	Organic acid	-	A	BC	B	A
MEK, methylisobutyl ketone	Ketone	B	X	X	CX	X
Menthol	Alcohol	A	A	A	X	A
Mercury	Mercury and derivatives	A	A	A	A	A
Mesitylene oxide	Ketone	BC	X	X	X	X
Methane	Hydrocarbon	CX	A	BC	X	A
Methyl acrylate	Ester	B	X	C	X	X
Methyl alcohol at 50 °C (122 °F)	Alcohol	A	A	A	A	CX
Methyl bromide	Brominated hydrocarbon	X	BC	X	X	A
Methyl chloride	Chlorinated hydrocarbon	C	X	X	X	AB
Methyl methacrylate	Ester	BC	X	CX	C	X
Methyl salicylate	Ester	B	X	X	-	-
Methylcyclopentane	Hydrocarbon	X	-	CX	X	AB
Methylene chloride	Chlorinated hydrocarbon	C	X	X	X	B
Milk	Food	A	A	A	A	A
Mineral oil	Mineral oil	X	A	B	B	A
Molasses	Food	A	A	A	A	A
Mono-di-tri-basic ammonium phosphate (aqueous solution)	Inorganic salt	A	A	A	AB	A
Monochlorobenzene	Chlorinated aromatic hydrocarbon	X	X	X	CX	AB
Monoethanolamine	Organic base	A	X	X	B	X
Monometilanilina	Aromatic organic base	AB	X	X	-	B
Monovinyl acetylene at -20 °C (68 °F)	Hydrocarbon	AB	A	B	BC	A
N						
Naphtha	Hydrocarbon	X	AB	C	X	A
Naphthalene at 80 °C (176 °F)	Aromatic hydrocarbon	X	CX	X	X	A
Naphthenic acid	Organic acid	X	B	X	-	A
Natural gas	Gas	X	A	A	BC	A
Nitric acid diluted at 10% at 50 °C (122 °F)	Inorganic acid	A	B	C	X	BC
Nitrobenzene at 50 °C (122 °F)	Aromatic nitroderivate	A	X	X	A	BC
Nitroethane	Nitroderivative	B	X	C	X	X
Nitromethane	Nitroderivative	B	X	C	X	X

A Bra - Utmärkt

B Rimligt - Bra

C Dålig

X Använd inte

KEMISK RESISTENS HOS GUMMIFÖRENINGARNA

Kontakta fluid	Typ	EPDM	NBR	CR	VMQ-PVMQ	FKM
O						
Octile adipate	Ester	B	X	X	C	AB
Octyl alcohol	Alcohol	BC	B	A	B	A
Oil at 150 °C (302 °F)	Hydrocarbon	X	BC	C	X	AB
Oil methyl	Ester	B	X	X	-	AB
Oil of ox feet	Oils	B	A	X	B	A
Oleic acid	Organic acid	BC	BC	BC	BC	-
Oleum	Inorganic acid	B	BC	C	CX	AB
Olive oil	Oils	C	A	B	A	A
Orthodichlorobenzene	Chlorinated aromatic hydrocarbon	X	CX	X	C	AB
Oxygen at 100 - 200 °C (212 - 392 °F)	Gas	C	X	X	B	B
Ozone (50pphm) at 40 °C (104 °F)	Gas	A	X	BC	A	A
P						
Palmitic acid	Organic acid	B	A	B	CX	A
Paradichlorobenzene	Chlorinated aromatic hydrocarbon	X	-	X	C	AB
Paraffin	Hydrocarbon	C	A	AB	-	A
Peanut oil	Oils	BC	A	BC	A	A
Perchlorethylene	Chlorinated hydrocarbon	X	BC	X	CX	A
Petrol 50% / Benzol 30% / Ethanol 20%	Aromatic hydrocarbon	X	C	CX	X	B
Petroleum	Hydrocarbon	X	A	B	BC	A
Phenol	Phenol	AB	X	CX	AB	A
Phenol at 100 °C (212 °F)	Phenol	B	X	X	B	B
Phenylhydrazine	Hydrazine	B	X	CX	X	A
Phosphoric acid 20%	Inorganic acid	A	B	B	BC	A
Phosphoric acid 85%	Inorganic acid	A	CX	AB	C	A
Phosphoric acid at 60% at 50 °C (122 °F)	Inorganic acid	A	C	B	-	A
Picric acid at 10% at 100 °C (212 °F)	Organic acid	AB	B	AB	X	A
Pine oil	Oils	X	B	X	X	A

A Bra - Utmärkt

B Rimligt - Bra

C Dålig

X Använd inte

KEMISK RESISTENS HOS GUMMIFÖRENINGARNA

Kontakta fluid

	Typ	EPDM	NBR	CR	VMQ-PVMQ	FKM
Pinene	Hydrocarbon	X	AB	C	X	A
Piperidine	Organic base	X	X	X	X	X
Polyvinyl acetate (emulsion)	Ester	A	-	B	-	-
Potassium acetate (aqueous solution)	Organic salt	A	B	B	X	X
Potassium chloride (aqueous solution)	Inorganic salt	A	A	A	A	A
Potassium hydrate at 70 °C (158 °F) (medium-high concentration)	Inorganic base	A	BC	B	C	X
Potassium nitrate (aqueous solution)	Inorganic salt	A	A	A	A	A
Potassium permanganate at 25% at 80 °C (176 °F) (water sol.)	Inorganic salt	C	X	B	A	CX
Potassium sulphate (aqueous solution)	Inorganic salt	A	A	A	A	A
Propilnitrat	Nitroderivative	B	X	X	CX	X
Propyl	Ester	B	X	X	CX	X
Propylene	Hydrocarbon	X	C	X	X	A
Propylene oxide	Hydrocarbon	B	X	X	X	X
Pydraul 10E, 29ELT	Fluid	A	X	X	X	A
Pydraul 115E	Fluid	A	X	X	X	A
Pydraul 230E, 312C, 540C	Fluid	X	X	X	X	A
Pydraul 30E, 50E, 65E, 90E	Fluid	A	X	X	A	A
Pydraul F9 at 80 °C (176 °F)	Fluid	B	X	X	A	A
Pyridine	Organic base	B	X	X	X	X
Pyrolegnous acid	Organic acid	B	X	B	-	-

R

Ragia water	Hydrocarbon	X	A	X	CX	A
Repent	Hydrocarbon	CX	A	B	X	A

S

Sea water	Water	A	A	A	A	A
Siliconic oil	Oils	A	A	A	C	A
Skydrol 500	Fluid	A	X	X	AB	X

A Bra - Utmärkt

B Rimligt - Bra

C Dålig

X Använd inte

KEMISK RESISTENS HOS GUMMIFÖRENINGARNA

Kontakta fluid	Typ	EPDM	NBR	CR	VMQ-PVMQ	FKM
Skydrol 7000	Fluid	A	X	X	A	X
Smoking nitric acid	Inorganic acid	X	X	X	X	CX
Soaps (solutions OF)	Soap	A	A	B	A	A
Sodium bisulphite (aqueous solution)	Inorganic salt	A	A	A	A	A
Sodium carbonate at 20% (aqueous solution)	Inorganic salt	A	A	A	A	A
Sodium chloride (aqueous solution)	Inorganic salt	A	A	A	A	A
Sodium hydrate at 70 °C (158 °F) (medium-high concentration)	Inorganic base	A	BC	AB	BC	C
Sodium metaphosphate (aqueous solution)	Inorganic salt	A	A	BC	-	A
Sodium peroxide	Inorganic peroxide	A	B	B	X	A
Sodium phosphate mono-di-tri-basico (water sol.)	Inorganic salt	A	A	AB	X	A
Sodium silicate (aqueous solution)	Inorganic salt	A	A	A	-	A
Sodium sulphate (aqueous solution)	Inorganic salt	A	A	A	A	A
Sodium thyo sulphate (aqueous solution)	Inorganic salt	A	B	A	A	A
Soja oil	Oils	C	A	BC	A	A
Stearic acid	Organic acid	B	B	B	A	AB
Stearic acid at 70 °C (158 °F)	Organic acid	B	B	B	A	-
Stearina at 70 °C (158 °F)	Organic acid	B	B	B	AB	A
Styrene	Aromatic hydrocarbon	X	X	X	C	B
Sulfate iron (aqueous solution)	Inorganic salt	A	A	A	AB	A
Sulfur dioxide	Inorganic anhydride	B	X	X	B	A
Sulfur dioxide	Inorganic anhydride	A	CX	C	BC	A
Sulfur exafluoride	Inorganic compound	A	AB	A	AB	A
Sulfuric acid	Inorganic acid	AB	B	B	CX	-
Sulfuric acid 50%	Inorganic acid	A	CX	C	X	A
Sulfuric acid concentr. 96% warm	Inorganic acid	C	X	X	X	B
Sulfuric acid diluted at 20%	Inorganic acid	A	B	AB	X	A
Super petrol	Hydrocarbon	X	B	CX	X	A

A Bra - Utmärkt

B Rimligt - Bra

C Dålig

X Använd inte

KEMISK RESISTENS HOS GUMMIFÖRENINGARNA

Kontakta fluid

Typ

EPDM

NBR

CR

VMQ- PVMQ

FKM

T

Tannic acid	Organic acid	C	C	AB	B	SA
Tannin	Phenol	A	A	AB	AB	A
Tar	Hydrocarbon	X	B	C	BC	A
Tartaric acid 20%	Organic acid	B	A	B	A	A
Terpineol	Alcohol	C	AB	X	-	A
Tetrabromoethane	Bromurated hydrocarbon	X	X	X	X	A
Tetrabutyl titanate	Titanium compound	A	AB	AB	-	A
Tetrachloroethane	Chlorinated hydrocarbon	X	X	X	X	AB
Tetraethyl lead	Lead compound	X	B	BC	C	A
Tetrahydrofuran	Ether	C	X	X	X	X
Tetraline	Hydrocarbon	X	CX	X	C	A
Thionyl chloride	Organic compound	C	X	X	X	B
Titanium tetrachloride	Titanium compound	X	C	X	X	A
Toluene	Aromatic hydrocarbon	X	CX	X	X	AB
Transformer oil	Oils	X	A	B	B	A
Triacetin	Ester	A	B	B	-	X
Tributylmercaptan	Mercaptan	X	X	X	X	A
Tributyl phosphite	Ester of phosphoric acid	AB	X	X	-	A
Tributyl	Ester	A	X	X	-	X
Trichlorethylene	Chlorinated hydrocarbon	X	X	X	X	AB
Trichloride phosphorus	Inorganic compound	A	CX	X	C	A
Trichloroacetic acid	Organic acid	B	B	C	-	C
Tricresyl phosphate	Ester of phosphoric acid	A	X	CX	B	A
Triethanolamine	Organic base	AB	BC	AB	-	X
Triethylamine	Organic base	CX	AB	C	CX	B
Trinitrotoluene	Nitroderivative	X	X	B	-	B
Triethyl	Ester of phosphoric acid	A	X	X	C	B
Turpentine essence	Hydrocarbon	X	A	X	X	A

U

Urea (aqueous solution)	Urea	A	A	A	A	A
-------------------------	------	---	---	---	---	---

A Bra - Utmärkt

B Rimligt - Bra

C Dålig

X Använd inte

KEMISK RESISTENS HOS GUMMIFÖRENINGARNA

Kontakta fluid	Typ	EPDM	NBR	CR	VMQ-PVMQ	FKM
V						
Vinagar	Organic acid	A	BC	B	A	C
Vinyl acetate	Ester	A	A	A	-	A
Vinyl chloride	Chlorinated hydrocarbon	C	X	X	X	A
Vinylidene chloride	Chlorinated hydrocarbon	X	BC	CX	X	B
W						
Water	Water	A	A	A	A	A
Water vapor above 150 °C (302 °F)	Vapor	B	X	X	X	CX
Water vapor at 125 °C - 150 °C (257 °F - 302 °F)	Vapor	AB	C	X	X	BC
Water vapor up to 125 °C (257 °F)	Vapor	A	B	BC	B	AB
Wet chlorine	Inorganic compound	C	C	C	X	AB
Wine	Alcoholic food	A	A	A	A	A
X						
Xylene	Aromatic hydrocarbon	X	CX	X	X	A
Xylidine	Aromatic organic base	C	BC	CX	X	X
Z						
Zinc acetate (aqueous solution)	Inorganic salt	A	B	B	X	X
Zinc chloride (aqueous solution)	Inorganic salt	A	A	A	A	A
Zinc sulphate (aqueous solution)	Inorganic salt	A	A	A	A	A

A Bra - Utmärkt

B Rimligt - Bra

C Dålig

X Använd inte

MPC Nordic

Saldivägen 16

175 62 Järfälla



+46 708 44 23 82



se@mpcindustries.com

